

EPOPLEX



LS50 *Viscosity vs. Temperature*

1000 East Park Avenue • Maple Shade, NJ 08052 • 856.667.8399 • FAX: 856.779.2963

EPOPLEX[®] LS50 - Viscosity (cP)

Temperature	Hardener	White	Yellow
70°F/21°C	17500	7100	8610
75°F/24°C	9690	4480	6200
80°F/27°C	6990	3060	3890
85°F/29°C	5110	2180	2890
90°F/32°C	3890	1660	2270
95°F/35°C	2730	1300	1650
100°F/38°C	2090	925	1250
105°F/41°C	1590	755	1010
110°F/43°C	1320	590	870
115°F/46°C	1050	475	710
120°F/49°C	720	395	580
125°F/52°C	575	335	500
130°F/54°C	435	290	490