



### EPOPLEX® LS65qs - Viscosity (cP)

| Temperature | Hardener | White | Yellow |
|-------------|----------|-------|--------|
| 85°F/29°C   | 6800     | 3750  | 3000   |
| 105°F/41°C  | 2110     | 1140  | 1310   |
| 120°F/49°C  | 1120     | 700   | 450    |
| 130°F/54°C  | 780      | 520   | 320    |
| 140°F/60°C  | 500      | 430   | 200    |

**Note:** Material temperatures below 140°F can be selected so that the viscosity of the components will coincide (within 10%), thus allowing for proper flow and mixing of the components.

**IMPORTANT:**

Epoplex® believes the information contained here to be true and accurate. Information contained here is for evaluation only. Epoplex makes no warranty, expressed or implied, based on this literature. We further reserve the right to modify and change products or literature at any time.

© 2021 Epoplex®  
05/2021

