


# EPOPLEX



## *Safe-T-Grip 2:1 Viscosity vs. Temperature*

1000 East Park Avenue • Maple Shade, NJ 08052 • 800.822.6920 • FAX: 856.779.2963

### EPOPLEX® Safe-T-Grip 2:1 - Viscosity (cP)

Temperature	Hardener	Epoxy
80°F/27°C	1585	780
90°F/32°C	935	500
100°F/38°C	585	340
110°F/43°C	360	250

**Note:** Material temperatures below 110°F can be selected so that the viscosity of the components will coincide (within 10%), thus allowing for proper flow and mixing of the components.

© 2019 Epoplex

a brand of  
**STONHARD®**